



Chandrabrabhu **E**nterprise **P**rivate **L**imited

HARDFACING WELDING WIRES

Name: CEPL-5001

Weld metal chemistry (with CO₂ shield)	C = 0.70%, Mn = 14.0%, Si = 0.80%, Ni = 0.20%, Cr = 2.30%	
Hardness (3 layers)	17–20 HRC (Work hardens)	
Size	1.60mm, 2.00mm, 2.40mm and 2.80mm	
Welding parameter guidelines (with CO₂ shield)	Size	Range
	1.6–2.0mm	200–350A, 26–28V
	2.4–2.8mm	250–400A, 28–30V
Wire extension (stickout)	30–40mm	

*CEPL
a gift to trust*